

## PTFE/Woven Fiberglass Laminates

### Features:


- Extremely Low Loss Tangent
- Excellent Dimensional Stability
- Product Performance Uniformity

### Benefits:

- Electrical Properties Are Highly Uniform Across Frequency
- Consistent Mechanical Performance
- Excellent Chemical Resistance

### Typical Applications:

- Military Radar Feed Networks
- Commercial Phased Array Networks
- Low Loss Base Station Antennas
- Missile Guidance Systems
- Digital Radio Antennas
- Filters, Couplers, LNAs



**DiClad** laminates are woven fiberglass/PTFE composite materials for use as printed circuit board substrates. Using precise control of the fiberglass/PTFE ratio, DiClad laminates offer a range of choices from the lowest dielectric constant and dissipation factor to a more highly reinforced laminate with better dimensional stability.

The woven fiberglass reinforcement in DiClad products provides greater dimensional stability than nonwoven fiberglass reinforced PTFE based laminates of similar dielectric constants. The consistency and control of the PTFE coated fiberglass cloth allows Arlon to offer a greater variety of dielectric constants and produces a laminate with better dielectric constant uniformity than comparable nonwoven fiberglass reinforced laminates. The coated fiberglass plies in DiClad materials are aligned in the same direction. Cross-plyed versions of many of these materials are available as Arlon CuClad materials.

**DiClad** laminates are frequently used in filter, coupler and low noise amplifier applications, where dielectric constant uniformity is critical. They are also used in power dividers and combiners, where low loss is important.

**DiClad 522 and DiClad 527** ( $\epsilon_r=2.40-2.65$ ) use a higher fiberglass/PTFE ratio to provide mechanical properties approaching conventional substrates. Other advantages include better dimensional stability and lower thermal expansion in all directions. The electrical properties of DiClad 522 and 527 are tested at 1MHz and 10GHz, respectively.

# Typical Properties: DiClad

Property	Test Method	Condition	DiClad 880	DiClad 870	DiClad 522/527
Dielectric Constant @ 10 GHz	IPC TM-650 2.5.5.5	C23/50	2.17, 2.20	2.33	2.40 to 2.65
Dielectric Constant @ 1 MHz	IPC TM-650 2.5.5.3	C23/50	2.17, 2.20	2.33	2.40 to 2.65
Dissipation Factor @ 10 GHz	IPC TM-650 2.5.5.5	C23/50	0.0009	0.0013	0.0018 <sup>1</sup>
Dissipation Factor @ 1 MHz	IPC TM-650 2.5.5.3	C23/50	0.0008	0.0009	0.0010
Thermal Coefficient of Er (ppm/°C)	IPC TM-650 2.5.5.5 Adapted	-10°C to +140°C	-160	-161	-153
Peel Strength (lbs.per inch)	IPC TM-650 2.4.8	After Thermal Stress	14	14	14
Volume Resistivity (MΩ-cm)	IPC TM-650 2.5.17.1	C96/35/90	1.4 x 10 <sup>9</sup>	1.5 x 10 <sup>9</sup>	1.2 x 10 <sup>9</sup>
Surface Resistivity (MΩ)	IPC TM-650 2.5.17.1	C96/35/90	2.9 x 10 <sup>6</sup>	3.4 x 10 <sup>7</sup>	4.5 x 10 <sup>7</sup>
Arc Resistance	ASTM D-495	D48/50	>180	>180	>180
Tensile Modulus (kpsi)	ASTM D-638	A, 23°C	267, 202	485, 346	706, 517
Tensile Strength (kpsi)	ASTM D-882	A, 23°C	8.1, 7.5	14.9, 11.2	19.0, 15.0
Compressive Modulus (kpsi)	ASTM D-695	A, 23°C	237	327	359
Flexural Modulus (kpsi)	ASTM D-790	A, 23°C	357	437	537
Dielectric Breakdown (kV)	ASTM D-149	D48/50	>45	>45	> 45
Density (g/cm <sup>3</sup> )	ASTM D-792 Method A	A, 23°C	2.23	2.26	2.31
Water Absorption (%)	MIL-S-13949H 3.7.7 IPC TM-650 2.6.2.2	E1/105 + D24/23	0.02	0.02	0.03
Coefficient of Thermal Expansion (ppm/°C) X Axis Y Axis Z Axis	IPC TM-650 2.4.24 Mettler 3000 Thermomechanical Analyzer	0°C to 100°C	25 34 252	17 29 217	14 21 173
Thermal Conductivity (W/mK)	ASTM E-1225	100°C	0.261	0.257	0.254
Outgassing Total Mass Loss (%) Collected Volatile Condensable Material (%) Water Vapor Regain (%) Visible Condensate (±)	NASA SP-R-0022A Maximum 1.00% Maximum 0.10%	125°C, ≤ 10 <sup>-6</sup> torr	0.01 0.01 0.01 NO	0.02 0.00 0.01 NO	0.02 0.00 0.01 NO
Flammability UL File E 80166	UL 94 Vertical Burn IPC TM-650 2.3.10	C48/23/50, E24/125	Meets requirements of UL94-V0	Meets requirements of UL94-V0	Meets requirements of UL94-V0


<sup>1</sup> Based on a Dielectric Constant of ≤ 2.50, Thickness ≥ 0.020”

## **Material Availability:**

DiClad laminates are supplied with 1/2, 1 or 2 ounce electrodeposited copper on both sides. Other copper weights and rolled copper foil are available. DiClad is available bonded to a heavy metal ground plane. Aluminum, brass or copper plates also provide an integral heat sink and mechanical support to the substrate.


When ordering DiClad products please specify dielectric constant, thickness, cladding, panel size and any other special considerations. Available master sheet sizes include 36" x 48" and 48" x 54".

# DiClad 527



**Figure 1**

Demonstrates the Stability of Dielectric Constant across Frequency. This information was correlated from data generated by using a free space and circular resonator cavity. This characteristic demonstrates the inherent robustness of Arlon Laminates across Frequency, thus simplifying the final design process when working across EM spectrum. The stability of the Dielectric Constant of DiClad over frequency ensures easy design transition and scalability of design.




**Figure 2**

Demonstrates the Stability of Dissipation Factor across Frequency. This characteristic demonstrates the inherent robustness of Arlon Laminates across Frequency, providing a stable platform for high frequency applications where signal integrity is critical to the overall performance of the application.


*Results listed above are typical properties; they are not to be used as specification limits. The above information creates no expressed or implied warranties. The properties of Arlon laminates may vary depending on the design and application.*

# DiClad 870



**Figure 3**

Demonstrates the Stability of Dielectric Constant across Frequency. This information was correlated from data generated by using a free space and circular resonator cavity. This characteristic demonstrates the inherent robustness of Arlon Laminates across Frequency, thus simplifying the final design process when working across EM spectrum. The stability of the Dielectric Constant of DiClad over frequency ensures easy design transition and scalability of design.




**Figure 4**

Demonstrates the Stability of Dissipation across Frequency. This characteristic demonstrates the inherent robustness of Arlon Laminates across Frequency, providing a stable platform for high frequency applications where signal integrity is critical to the overall performance of the application.


Results listed above are typical properties; they are not to be used as specification limits. The above information creates no expressed or implied warranties. The properties of Arlon laminates may vary, depending on the design and application.

# DiClad Series 880



**Figure 5**

Demonstrates the Stability of Dielectric Constant across Frequency. This information was correlated from data generated by using a free space and circular resonator cavity. This characteristic demonstrates the inherent robustness of Arlon Laminates across Frequency, thus simplifying the final design process when working across EM spectrum. The stability of the Dielectric Constant of DiClad over frequency ensures easy design transition and scalability of design.



**Figure 6**

Demonstrates the Stability of Dissipation across Frequency. This characteristic demonstrates the inherent robustness of Arlon Laminates across Frequency, providing a stable platform for high frequency applications where signal integrity is critical to the overall performance of the application.

Results listed above are typical properties; they are not to be used as specification limits. The above information creates no expressed or implied warranties. The properties of Arlon laminates may vary, depending on the design and application.



**MATERIALS FOR ELECTRONICS**

---

**CONTACT INFORMATION:**

---

For samples, technical assistance, customer service or for more information, please contact Arlon Materials for Electronics Division at the following locations:

**NORTH AMERICA:**

Arlon LLC  
Electronic Substrates  
9433 Hyssop Drive  
Rancho Cucamonga, CA 91730  
Tel: (909) 987-9533  
Fax: (909) 987-8541

Arlon LLC  
Microwave Materials  
1100 Governor Lea Road  
Bear, DE 19701  
Tel: (800) 635-9333  
Outside U.S. & Canada: (302) 834-2100  
Fax: (302) 834-2574

**EUROPE:**

Arlon LLC  
44 Wilby Avenue  
Little Lever  
Bolton, Lancaster BL31QE  
United Kingdom  
Tel: (44) 120-457-6068  
Fax: (44) 120-479-6463

**SOUTHERN CHINA:**

Arlon LLC  
Room 805, Unit 3, Bldg 4  
Liyuan, Xincun Holiday Road  
Huaqiao Cheng, Shenzhen 518053  
China  
Tel/Fax: (86) 755-269-066-12

**NORTHERN CHINA:**

Arlon LLC.  
Room 11/401, No. 8  
Hong Gu Road  
Shanghai, China 200336  
Tel/Fax: (86) 21-6209-0202

© 2008, 2009 Arlon LLC

2007 Rev c

Or visit us on the web at:  
[www.arlon-med.com](http://www.arlon-med.com)

